

NC ALCOHOLEATED SEPCIFICATION E21(E620)

TESTS	SPESECIFICATION
Nitrogen Content (%)	10.7-11.2
Viscosity (DIN 53179)	400±25CPS
B&J Stability Test in 132 ± 0.2 ° C (ml/gr)	MAX 1.5
Moisture(%)	MAX 4
Damping Medium (Ethanol)	30 ± 2 %
Acidity % (as H2SO4) Dry NC	MAX 0.065

Measuring viscosity according DIN 53179:

Measuring instrument: Hoeppler viscometer precisin model,ball 4 with viscosity solution (see I).

I. For preparation viscosity solution mixing 21% by weight dry solid without plastizier NC E21(E620) with 79% by weight solvent.

(solvent: 95% by weight Acetone +5% by weight water)

Measuring temperature: 25° c

Standard range for viscosity according DIN53179:400cps ± 25cps

Main Applications :

Car lacquers, railway carriage, exterior finishing, film laquers,exterior combination lacquers, nitrocellulose surface etc,Wood laquers, polishing and buffing lacquers.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,

Shahnazari Ave, Madar SQ, Tehran, Iran

Tel: +9821 2225 69 21 Fax: +9821 2225 91 71

Email: info@caspianro.com

Website: www.caspianro.com