

ALKYD RESIN LCSO 603W65

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in white spirit : Z ₂ -Z ₄ /35-70 stock
Color Index	(%60 solution in white spirit) Gardner color standard 1933<6
Acid value	DIN 53183(mg koH/g of solid resin) 6-10
Density	20 ° c (g/ml) approx : 0.92-0.94
Solid %	%65 ± %1
Characteristics	Long Oil, air drying alkyd resin Type of oil : soya bean Form of supply : %65 solution in white spirit
Properties	Excellent drying and non yellowing properties.Very good brushability & color retention. Good interior and exterior durability.
Resin Composition (approx)	%60 OIL (Triglyceride) %24 phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax:+9821 2225 91 71
Email:info@caspiantro.com
Website: www.caspiantro.com