

ALKYD RESIN SCCO 281X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : Z ₆ -Z ₇ /140-220 stock
Color Index	(%60 solution in xylene) Gardner color standard 1933:<6
Acid value	DIN 53183(mg koH/g of solid resin) 6-10
Density	20 ° c (g/ml) approx : 1.08-1.1
Solid %	%60 ± %1
Characteristics	Short Oil, non drying alkyd resin Type of oil : tall oil Form of supply : %60 solution in xylene
Properties	Very good adhesion and felexibility, good compatibility with nitrocellulose and amino resins.
Resin Composition (approx)	%28 OIL (Triglyceride) %42 phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71
Email: info@caspiantro.com
Website: www.caspiantro.com