

## ALKYD RESIN SCSO 261X60

|                                   |  |
|-----------------------------------|--|
| <b>Viscosity</b>                  | Gardner Bubble viscometers/25 ° c<br>60% solution in xylene : $Z_5 - Z_6 / 100-110$ stock                  |
| <b>Color Index</b>                | (%60 solution in xylene)<br>Gardner color standard<br>1933<6   |
| <b>Acid value</b>                 | DIN 53183 mg koH/g of solid resin < 20   |
| <b>Density</b>                    | 20 ° c (g/ml) approx : 1.12-1.14   |
| <b>Solid %</b>                    | %60 ± % 1  |
| <b>Characteristics</b>            | Short Oil, non drying alkyd resin<br>type of oil : linseed soya<br>form of supply : %60 solution in Xylene |
| <b>Properties</b>                 | Good compatibility with nitrocellulose and amino resins, very good adhesion to steel and flexibility.      |
| <b>Resin Composition (approx)</b> | %26 OIL (Triglyceride)<br>%40 Phthalic anhydride   |

### Dilutability

| White spirit | Xylene | Toluene | Acetone | M.I.B.K | Ethylglycol | Butylacetate | N-Butanol |
|--------------|--------|---------|---------|---------|-------------|--------------|-----------|
| ✓            | ✓      | ✓       | ✓       | ✓       | ✓           | ✓            | ✓         |



#### Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,  
Shahnazari Ave, Madar SQ, Tehran, Iran  
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71  
Email: info@caspiantro.com  
Website: www.caspiantro.com