

## ALKYD RESIN SCSU 371X60

<b>Viscosity</b>	Gardner Bubble viscometers/25 ° c 60% solution in xylene : $Z_5 - Z_6$ /80-120 stock
<b>Color Index</b>	(%60 solution in xylene) Gardner color standard 1933:<4
<b>Acid value</b>	DIN 53183(mg koH/g of solid resin) 6-10
<b>Density</b>	20 ° c (g/ml) approx : 1.04-1.06
<b>Solid %</b>	%60 ± %1
<b>Characteristics</b>	Short Oil, non drying alkyd resin Type of oil : tall oil Form of supply : %60 solution in xylene
<b>Properties</b>	Good adhesion to steel, good flexibility, excellent color and gloss retention, good compatibility with nitrocellulose and amino resins.
<b>Resin Composition (approx)</b>	%37 OIL (Triglyceride) %38 Phthalic anhydride

### Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



#### Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,  
Shahnazari Ave, Madar SQ, Tehran, Iran  
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71  
Email: info@caspiantro.com  
Website: www.caspiantro.com