

NITROCELLULOSE PUTTY

Product description	It is fast drying, easy sanding and filling power for all wood surface and cars	
Technical information	1) Surface dry	10 min at 25 ° c
	2) Completed dry	30 min
	3) Solid content	68±1
	4) Sepecific gravity	1.49±0.05 gr/cm ³
	5) Viscosity at 25 ° c	3267 c.p
	6) Application method	Spray brush
	7) Cover rate	8-10 m ² /1kg
	8) Time to recoat	60 min
Surface preparations	Surface should be clean and free of dust, grease, and oil.	



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax:+9821 2225 91 71
Email:info@caspiantro.com
Website: www.caspiantro.com